

Hot and Cold Rolling Industry

Plasma (Ion) Nitriding in the Hot and Cold Rolling Industry



Parts:

- **Rolls** for Shape Rolling (Roll Forming)
- **Mandrel and Rolls** for Ring Rolling
- **Mandrel and Rolls** for Tube (Roll) Piercing
- **Rolling Dies** for Gear Rolling
- **Rolling Dies** for Skew Rolling

Transmission parts in mechanisms of the Rolling machines – see Transmissions and Drive Systems Industry

Requirements:

- For high **Hardness**
- For high **Wear resistance**
- For high **Fatigue strength**
- For **Plastic deformation resistance**
- For **Thermal fatigue resistance**

Ion Nitriding Solutions:


- **Significantly increasing the surface hardness, wear (abrasive and adhesive) resistance and fatigue life of the tools, improving their lifespan and performance.**
- **Improving the thermal fatigue resistance** of the tools.
- **Reducing the friction coefficient.**
- **Increasing the corrosion resistance.**

Improving these parameters **will save from downtime and maintenance costs.**

Steel Grades Used:

Steel Grade	Surface Hardness, HV	Case Depth, um
H-13 / X40CrMoV5-1/ SKD61	900 - 1200	40 - 200
H-11 / X37CrMoV5-1	900 - 1200	40 - 200
H-21/X30WCr-V3/ SKD5	850 - 1000	50 - 250
M2 / HS 6-5-2 / 1.3343	1000 - 1300	40 - 150
M42 / HS 2-9-1-8 / 1.3247	1000 - 1300	40 - 150
T15 / HS 12-0-5-5 / 1.3202	1000 - 1300	40 - 150
D2 / X153CrMoV12 / SKD 11	900 - 1200	40 - 150
D3 / X210Cr12 / SKD 1	1000 - 1200	50 - 200
A2 / X100CrMoV5 / SKD12	800 - 1000	50 - 200
AC100	700 - 900	100 - 250
ASP-23 / S790	1000 - 1300	50 - 250
1.2379	900 - 1100	50 - 200
4142 / 42CrMo4	650 - 750	150 - 400

- Hardness and depth values are recommended for the industry and exact values will depend on the nitriding process parameters.
- This is not a full list of used steel grades



- Example of H13 tool steel after Ion Nitriding - surface hardness and diffusion depth



Equipment and Technology

Developed state of the art both Hot-Wall and Cold-Wall furnaces for Plasma (Ion) Nitriding.

Know-How and Expertise

We share our knowledge and expertise on nitriding different steel grades and parts, gathered for more than 45 years.

Support

We give full-time support.



Ionitech Ltd.

5 Capitan Ljuben Kondakov st.,
Sofia 1582, Bulgaria
Mobile: +359 887 80 9272
Mobile: +359 889 36 4364
Email: office@ionitech.com
www.ionitech.com